

Lab Test Report n°: **25WL0096381** of **25/09/2025**

Customer.
AGRIBIOMASS SRL
Via Cappuccini Vecchi, 2
62014 Corridonia MC

Receipt Date in Lab: 26/08/2025
Test Beginning Date: 27/08/2025
Test Result Date: 25/09/2025

Sample's data provided by the client

Matrix: Solid biofuels
Description: Wood pellet - 2095UKR
Sample Weight: 15 Kg
Supplier: "AVANTAGE-CAPITAL" LLC
Origin: 1.1.3

Sampling data provided by the client

Effected By: customer
Technician: Carlotta Tozzato
Sampling Date: 18/07/2025
Site: Zhytomyr

Test Method	Result	Uncertainty	U.M.	LOQ	Class A1	Class A2	Class B
* o Nitrogen UNI EN ISO 16948:2015	< 0,1		w-% d.m.	0,1			
* o Chlorine UNI EN ISO 16994:2017 Met A + UNI EN ISO 10304-1:2009	< 0,01		w-% d.m.	0,01			
* o Sulphur UNI EN ISO 16994:2017 Met A + UNI EN ISO 10304-1:2009	0,01	±0,01	w-% d.m.	0,01			
Diameter UNI EN ISO 14780:2019 + UNI EN ISO 17829 : 2016	6,3	±0,3	mm		5÷7	5÷7	5÷7
Mean length UNI EN ISO 14780:2019 + UNI EN ISO 17829 : 2016	13,9	±1,8	mm	3,1	3,15÷40	3,15÷40	3,15÷40
* Pellets with length <= 10 mm UNI EN ISO 14780:2019 + UNI EN ISO 17829 : 2016	7,6	±1,0	w-%	0,1			
* Pellets with length > 40mm UNI EN ISO 14780:2019 + UNI EN ISO 17829 : 2016	< 0,1		w-%	0,1	1	1	1
* Pellets with length > 45 mm UNI EN ISO 14780:2019 + UNI EN ISO 17829 : 2016	0		Number	0	0	0	0
Moisture UNI EN ISO 14780:2019 + UNI EN ISO 18134-1:2022	7,4	±0,4	w-%	1,0	10,0	10,0	10,0
Ash at 550° UNI EN ISO 14780:2019 + UNI EN ISO 18122 : 2023	0,50	±0,06	w-% d.m.	0,10	0,70	1,20	2,00
Mechanical durability UNI EN ISO 14780:2019 + UNI EN ISO 17831-1:2016	98,8	±0,3	w-%		>= 98,0	>= 97,5	>= 96,5
Fines (< 3,15 mm) (bags) (as received) UNI EN ISO 14780:2019 + ISO 18846:2016	0,5	±0,1	w-%	0,1	0,5	0,5	
Coarse pellet fines UNI EN ISO 14780:2019 + ISO 18846:2016	0,2	±0,1	w-%	0,1			
o Net calorific value ISO 18125:2018	5,0	±0,2	kWh/kg	1,0			>= 4,6

Page 1 of 3



Water & Life Lab srl
(Groupe Carso) - Società unipersonale

Laboratory with quality management system certified according to the regulation
UNI EN ISO 9001: 2015 by DNV. Certificate n ° 267539-2018-AQ-ITA-ACCREDIA

Via Enrico Mattei n°37
24060 - Entratico (BG) - ITALY
+39 035.940665
info@waterlifelab.it
www.waterlifelab.it

Capitale sociale 50.000 € i.v.
C.F. / P.IVA 01855020168
r.e.a. n. 242620



00082

Follows Lab Test Report n°: **25WL0096381** of **25/09/2025**

Test Method	Result	Uncertainty	U.M.	LOQ	Class A1	Class A2	Class B
* ₀ higher calorific value ISO 18125:2018	5,3	±0,2	kWh/kg	1,0			
Particle density UNI EN ISO 14780:2019 + ISO 18847:2024	1,18	±0,04	g/cm3	0,10			
Bulk density UNI EN ISO 14780:2019 + UNI EN ISO 17828:2025	650	±27	kg/m3	10	600÷750	600÷750	600÷750
* Additives (data provided by the customer)	absent		%				
* ₀ Fusibility of the ashes (pre-ashing temperature 815°C) NF EN ISO 21404:2020							
* ₀ Shrinkage temperature NF EN ISO 21404:2020	1070	±48	°C				
* ₀ Deformation temperature NF EN ISO 21404:2020	> 1500		°C		>= 1200	>= 1100	>= 1100
* ₀ Flow temperature NF EN ISO 21404:2020	> 1500		°C				
* ₀ Hemisphere temperature NF EN ISO 21404:2020	> 1500		°C				
Arsenic UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	< 0,4		mg/kg d.m.	0,4	1	1	1
Cadmium UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	< 0,2		mg/kg d.m.	0,2	0,5	0,5	0,5
Chromium UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	0,4	±0,1	mg/kg d.m.	0,2	10	10	10
Mercury UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	< 0,04		mg/kg d.m.	0,04	0,1	0,1	0,1
Nickel UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	0,2	±0,1	mg/kg d.m.	0,2	10	10	10
Lead UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	< 0,2		mg/kg d.m.	0,2	10	10	10
Copper UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	0,9	±0,3	mg/kg d.m.	0,4	10	10	10
Zinc UNI EN ISO 14780:2019 + UNI EN ISO 16968:2015 + UNI EN ISO 22036:2024	8,9	±1,5	mg/kg d.m.	2,0	100	100	100

Limit: Limits ISO 17225-2 (6mm)

LOQ: limit of quantification; U.M.: unit of measure

>lim: the parameters indicated by the symbol on the side are out of limits.

(*) : The starred Tests are not ACCREDIA qualified



Follows Lab Test Report n°: 25WL0096381 of 25/09/2025

(°): The analyzes are performed by an external laboratory

Determinations of Nitrogen, Chlorine and Sulphur were carried out by an COFRAC accredited laboratory with number 1-0273.

The container used for the determination of the bulk density complies with the requirements of point 5.1.3 of the method.

The result of Pellet length is the average of 50 measurements and the standard deviation calculated is 3.66.

The result of Pellet diameter is the average of 10 measurements and the standard deviation calculated is 0.08.

For the division of the sample, paragraph 8.6 of the UNI EN ISO 14780: 2019 standard has been applied.

The Mass of the Test portion for the determination of fines is 7238 g.

Determinations of Net calorific value and Gross calorific value were carried out by an COFRAC accredited laboratory with number 1-0273.

The digestion of the sample intended for metal analysis has been performed with hydrogen peroxide and nitric acid.

The determination of the metals has been performed in ICP-OES.

Determinations of ash fusion, temp. of contraction, temp. of deformation, temp. of hemisphere, temp. slides were carried out by an COFRAC accredited laboratory with number 1-0273.

Notes:

Uncertainty is expressed in the units of measurement of the parameter to which they refer. The coverage factor is $k = 2$ with a 95% probability range.

For microbiological analysis, expressed on all matrix except waters, combined standard uncertainty is estimated according ISO 19036 as intralaboratory reproducibility standard deviation.

For qualitative microbiological analysis, the expression of the result as "detected/not detected" means presence or absence of confirmed colony of the microorganism.

Water & Life Lab S.r.l. is registered, to the Lombardy Region Register of the laboratories that are authorized to perform analysis in the field of the self-control procedures of food industries with the progressive number 030016301004 (based on the General Health Management act number 893 of February 2nd 2011).

The Laboratory does not consider the rounding of the data and the uncertainty of measurement in comparison with the limits that may be applied in the Test Report.

The results reported in this test report refer to the sample as received, the laboratory declines all responsibility for the sample data provided by the client.

The results reported on this lab test report are exclusively referred to the tested sample.

The end date of the analyses reported at the top of the test report includes the verification and control activities of the analytical data detected

This Lab Test Report can be reproduced fully only. The partial reproduction of this Lab Test Report is admitted only after the written authorization of the Water & Life Lab S.r.l. laboratory responsible.

Laboratory Manager
P.I. Enio Belotti

Scientific Direction
dr. Angelo Carlessi

Order of Chemists and Physicists of
Bergamo
Chemist Section.A
registration n°146

This Test Report is signed with a digital signature in accordance with current legislation.
Files in PDF format or paper printouts of the Test Report have no legal value.
To verify the authenticity of the Test Report it is important to have the file in .p7m format which is sent by the Laboratory.

End of the test report n° 25WL0096381

